

COOLING TOWER FAN BLADES REPAIRED WITH BELZONA PRODUCTS

ID: 1445



PROBLEM

Erosion on leading edges, cracks and flaking on trailing edges of cooling tower fan blades caused by UV degradation, erosion and impingement. This reduces the overall efficiency and operation of the cooling system.

APPLICATION SITUATION

GRP fan blades from cooling tower

APPLICATION METHOD

The application was carried out in accordance with Belzona Know-How System Leaflet FBC-1. The Leading edges and trailing edges were rebuilt with Belzona® 1311 and subsequently coated with Belzona® 1321. Blade body was coated using Belzona® 5811.

BELZONA FACTS

The Belzona refurbishment has avoided the high cost of blade replacement. Each cell contains six blades. The Belzona solution will provide the plant with long term protection of the blades.

INDUSTRY

General Industry

LOCATION

Fertilizer Producer, Indonesia

APPLICATION DATE

February 2010

PRODUCTS

Belzona 1311 (Ceramic R Metal)
Belzona 1321 (Ceramic S Metal)
Belzona 5811 (Immersion Grade)

SUBSTRATE

GRP

PHOTOS

1. Damage on leading edges
2. Flaking on trailing edges
3. Belzona application
4. Completed blades after coating with Belzona 1321 and Belzona 5811

For more examples of Belzona Know-How in Action, please visit khia.belzona.com

Belzona products are manufactured
under an ISO 9001 Registered
Quality Management System.

www.belzona.com

