

BELZONA REPAIRS AND PROTECTS CORRODED SHELL

ID: 566



PROBLEM

Shell and dished end were highly corroded due to chemical attack that resulted in critical wall thickness reduction in the shell.

APPLICATION SITUATION

Heat exchanger shell

APPLICATION METHOD

Application was carried out in accordance with Belzona Know-How System Leaflets HEX-2 and HEX-3. Belzona® Marine Metal was used to restore the original dimensions then Belzona® 1321 was used to protect the restored area from any further corrosion.

BELZONA FACTS

Repair completed quickly and safely, thickness of the shell was restored to the original dimensions with no heat and no special tools. As measured weekly, the vessel stopped losing wall thickness, resisting chemical attack and still in excellent condition.

INDUSTRY

Chemical & Petrochemical

LOCATION

Petrochemical facility, Egypt

APPLICATION DATE

January 2004

PRODUCTS

Belzona Marine Metal
Belzona 1321 (Ceramic S-Metal)

SUBSTRATE

Carbon steel

PHOTOS

1. General view of the shell and cover.
2. The corroded surface inside the shell.
3. Forming the applied Belzona Marine Metal.
4. Belzona Marine Metal rebuild successfully completed. Belzona 1321 applied to provide overall corrosion protection.

For more examples of Belzona Know-How in Action, please visit khia.belzona.com

Belzona products are manufactured under an ISO 9001 Registered Quality Management System.

www.belzona.com

