


BELZONA REPAIRS 82 EXPANSION JOINTS ON A PRIMARY SETTLEMENT TANK

ID: 7529



PROBLEM

Existing expansion joints had failed. The customer then tried to use a cementitious material to repair them but this also cracked and failed.

APPLICATION SITUATION

The customer's Primary Settlement Tank was unable to operate efficiently and the tank's arm was struggling to rotate, which could have caused further damage to the equipment.

APPLICATION METHOD

The nosings of the joints were rebuilt using Belzona 4111 and Belzona 2211 used as the expansion joint material. The application was carried out in accordance with Belzona System Leaflets FPA-5 and FPA-7.

BELZONA FACTS

The primary settlement tanks' original concrete design failed within four years due to water ingress. Belzona materials are resistant to this type of damage and so will last for many more years to come. This was one of the clients only options to keep the equipment in operation.

INDUSTRY

Water / Wastewater

LOCATION

Bedford, UK

APPLICATION DATE

August 2017

PRODUCTS

- Belzona 4111 (Magma-Quartz)
- Belzona 2211 (MP Hi-Build Elastomer)

SUBSTRATE

Concrete

PHOTOS

1. The settlement tank.
2. A damaged expansion joint.
3. Nosings rebuilt using a former.
4. Completed expansion joint.

For more examples of Belzona Know-How in Action, please visit khia.belzona.com

Belzona products are manufactured under an ISO 9001 Registered Quality Management System.

www.belzona.com

